

Easy-Mix RK-7000 Structural Acrylic Adhesive



slow-curing
high strength
impact resistant, residual elasticity

RK-7000 can be used to bond numerous materials such as plastics, metals and ceramics to themselves and among. It is particularly convenient for structural bondings if high-strength connections are required. The adhesive is very viscous and is therefore suitable also for applications on vertical surfaces.

WEICON RK-7000 can be used universally and, for example, in plastics technology, metal construction, car body and vehicle construction, machine construction, electrical engineering, wood processing and in trade show and exhibition construction.

Technical Data

Base	Methyl methacrylate
Colour after curing	cream white, milky
Mixing ratio resin/hardener	1:1
Colour after curing	creme white, milky
Density of the mixture	0,98 - 1,02 g/cm ³
Viscosity of the mixture	40.000 - 60.000 mPa·s
Application procedure	Easy-Mix
Composition	viscous
Pot-life at +20°C (+68°F)	15 min.
Handling strength (35% strength) after	40 min.
Capable of bearing mechanical loads (50% strength) after	60 min.
Processing temperature	+10 to +40 °C
Curing temperature	+18 °C

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Final strength (100%) after	12 h
Adhesive gap bridging	0,1 - 5,0 mm
Shear strength according to DIN 53281 at:	
Aluminium	20 N/mm ²
Steel sand blasted	23 N/mm ²
Stainless Steel	22 N/mm ²
PC	11 N/mm ²
PMMA	9 N/mm ²
ABS	7 N/mm ²
Hard-PVC	12 N/mm ²
GRP	21 N/mm ²
CRP	22 N/mm ²
Polyamide 6.6	1 N/mm ²
Temperature resistance	-55 to +125 °C
ISSA-Code	75.629.55
IMPA-Code	81 29 94

Surface pre-treatment

The prerequisite for perfect adhesion are clean and dry surfaces (e.g. cleaning and degreasing with WEICON Cleaner Spray S or WEICON Plastic Cleaner). The best results are achieved when the surfaces to be bonded are mechanically roughened. The adhesive is applied only on one side.

Processing

WEICON Easy-Mix products can be processed directly from the double cartridges with the help of the included static mixer. Reject the first 5 cm of the dosed bead. Apply adhesive to only one of the surfaces to be bonded. The pot life given is for a material quantity of 10 ml at room temperature. If larger quantities are used, the curing time will be faster. Similarly, higher ambient temperatures shorten the cure times (as a rule of thumb, every +10°C increase above room temperature will halve working and curing time). Temperatures below +16°C will extend working and curing times considerably, while below about +5°C, no reaction will take place at all.

Storage

The shelf life is 12 months when stored unopened at a normal climate (+23°C and 50 % rel. humidity).

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weiconcz.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

Technical Datasheet

Create Date: 17.11.2017 - Seite 2/2

Available sizes:

10565050 Easy-Mix RK-7000 Structural Acrylic
Adhesive 50 ml

Accessories:

10650005 Mixing Nozzles Easy-Mix, Quadro
10653050 Dispenser D 50,
11202400 Sealant and Adhesive Remover, 400 ml
11207400 Surface Cleaner, 400 ml
11850200 Hand Protective Foam, 200 ml
12955175 Dosing Tips, Typ A Size 0,5

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weiconcz.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es