

Plastic-Bond



excellent adhesion on plastics
high strength
shock and impact resistant

WEICON Plastic-Bond is a solvent-free structural adhesive with very good adhesion to plastics, aluminum, steel and much more. The adhesive is suitable for static as well as dynamic loads, has a high impact and peel strength and a maximum gap filling capacity of 5 mm.

Plastic-Bond is particularly suitable for structural bondings where high strength connections are required. It has a high viscosity and is suitable for processing on vertical surfaces.

The structural adhesive is universally applicable and can be used, for example, in plastics technology, in metal construction, in car body and vehicle construction, in mechanical engineering, in electrical engineering, in wood processing or in construction works at exhibitions.

Technical Data

Base	Methyl methacrylate
Colour after curing	cream white, milky
Mixing ratio resin/hardener	1:1
Density of the mixture	0,98 - 1,02 g/cm ³
Viscosity of the mixture	40.000 - 60.000 mPa·s
Application procedure	A-B-method
Composition	thixotropic
Pot-life at +20°C (+68°F)	15 min.
Handling strength (35% strength) after	40 min.
Capable of bearing mechanical loads (50% strength) after	60 min.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Processing temperature	+10 to +40 °C
Curing temperature	+18 °C
Final strength (100%) after	12 h
Adhesive gap bridging	0,1 - 5,0 mm
Shear strength according to DIN 53281 at:	
Aluminium	20 N/mm ²
Steel sand blasted	23 N/mm ²
Stainless Steel	22 N/mm ²
PC	11 N/mm ²
PMMA	9 N/mm ²
ABS	7 N/mm ²
Hard-PVC	12 N/mm ²
GRP	21 N/mm ²
CRP	22 N/mm ²
Polyamide 6.6	1 N/mm ²
Temperature resistance	-55 to +125 °C

Surface pre-treatment

The prerequisite for perfect adhesion are clean and dry surfaces (e.g. cleaning and degreasing with WEICON Surface Cleaner). The best results are achieved when the surfaces to be bonded are mechanically roughened. The adhesive is applied only on one side.

Processing

Plastic-Bond can be processed directly from the double cartridge. Reject the first centimetre of the dosed bead. Mix the product thoroughly. Apply adhesive mixture quickly to only one of the surfaces to be bonded. Join both surfaces immediately afterwards.

Storage

The shelf life is 12 months when stored unopened at a normal climate (+23°C and 50 % rel. humidity).

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

10565024 Plastic-Bond 24 ml

Accessories:

10650005 Mixing Nozzles Easy-Mix, Quadro
 11207400 Surface Cleaner, 400 ml
 11850200 Hand Protective Foam, 200 ml
 12955175 Dosing Tips, Typ A Size 0,5

WEICON GmbH & Co. KG
 (Headquarters)
 Germany
 phone +49 (0) 251 9322 0
 info@weicon.de

WEICON Middle East L.L.C.
 United Arab Emirates
 phone +971 4 880 25 05
 info@weicon.ae

WEICON Inc.
 Canada
 phone +1 877 620 8889
 info@weicon.ca
 www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
 Turkey
 phone +90 (0) 212 465 33 65
 info@weicon.com.tr
 www.weicon.com.tr

WEICON Romania SRL
 Romania
 phone +40 (0) 3 65 730 763
 office@weicon.com

WEICON SA (Pty) Ltd
 South Africa
 phone +27 (0) 21 709 0088
 info@weicon.co.za

WEICON South East Asia Pte Ltd
 Singapore
 phone (+65) 6710 7671
 info@weicon.com.sg

WEICON Czech Republic s.r.o.
 Czech Republic
 phone +42 (0) 417 533 013
 info@weiconcz.cz

WEICON Ibérica S.L.
 Spain
 phone +34 (0) 914 7997 34
 info@weicon.es