

# Flex+bond® Liquid



## Self-levelling, one-component casting and coating mass

Flex+Bond Liquid is a self-levelling mass for casting and coating works with a layer thickness of up to 10mm.

It cures without any odour, is based on MS-Polymer and is free of solvents, isocyanates and silicone.

It can be used for many different applications, such as castings in the electrical and electronics industry or casting of cable connections. It is also suitable for the insulation technology, for metal, tank and machinery and valve construction and in the ventilation and air conditioning technology.

## Technical Data

Composition	One-component MS-polymer
Color	white
Density	1,48 g/cm <sup>3</sup>
Viscosity	7.000
Processing temperatur	+5 to +40 °C
Curing type	by humidity
Curing condition	+5°C to +40°C and 30% to 95% rel. humidity
Skin-overtime*	40 min.
Curing speed (first 24h)	2 - 3 mm
Volume change (DIN 52451)	-9 %
Gap filling up to max.	0,5 mm
Gap width up to max.	25 mm
Shore A hardness (DIN 5355 / ASTM D 224) ± 5	43
Elongation at break (DIN 53504/ASTM D 2240) ± 5	400 %
Tensile strength of pure adhesive and sealant	2,2 N/mm <sup>2</sup>
Average tensile shear strength (DIN 53283 / ASTM D 12)	1,8 N/mm <sup>2</sup>
Tear strength (DIN 53515/ASTM D 1002)	11 N/mm <sup>2</sup>
Movement capacity max.	10 %
Overpaintable (liquid paint)	after complete curing

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Building material category (DIN 412)	B2
Specific forward resistance	1,1 x 10 <sup>12</sup> Ohm/cm
Temperature resistance	-40 to +80 briefly, to +120 °C

\*Measured at 50% relative air humidity and +23°C

## Surface pre-treatment

The surfaces must be clean and free of grease. Many surface contaminants, e.g. oil, dust and dirt, can be removed with WEICON Surface Cleaner. For heavily soiled metal surfaces, we recommend WEICON Cleaner Spray S; WEICON Sealant and Adhesive Remover is suitable for removing old paint or adhesive residues. Most materials can be bonded well to themselves and among each other. For certain materials or extreme requirements, we recommend the use of an adhesion agent (primer). Detailed information on this subject is contained in the primer selection table. A mechanical surface pre-treatment, e.g. sanding or sand-blasting, can considerably improve the adhesion.

## Processing

Squeeze out by hand.

Close tube again immediately after use, opened tubes should be used as quickly as possible.

## Storage

When unopened and stored at room temperature (+23°C and 50 % rel. humidity), WEICON elastic one-component adhesives and sealants have a shelf life of 12 months.

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Available sizes:

13354085 Flex+bond® Liquid 85 ml liquid

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weiconcz.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es